

Santoprene™ 111-45

Thermoplastic Vulcanizate

Product Description	Key Features
A soft, black, versatile thermoplastic vulcanizate (TPV) in the thermoplastic elastomer (TPE) family. This material combines good physical properties and chemical resistance for use in a wide range of injection molding applications. This grade of Santoprene TPV is shear-dependent and can be processed on conventional thermoplastics equipment for injection molding. It is polyolefin based and completely recyclable.	<ul style="list-style-type: none"> Recommended for applications requiring excellent flex fatigue resistance. Excellent ozone resistance. UL listed: file #QMFZ2.E80017, Plastics - Component; file #QMFZ8.E80017, Plastics Certified For Canada - Component. Used in sealing applications. EU Directive 2002/95/EC (RoHS) compliant.

General			
Availability ¹	<ul style="list-style-type: none"> Africa & Middle East Asia Pacific 	<ul style="list-style-type: none"> Europe Latin America 	<ul style="list-style-type: none"> North America South America
Applications	<ul style="list-style-type: none"> Automotive - Air Filter Gaskets Automotive - HVAC Flapper Door Seals Automotive - Motor Brush Holders Automotive - Plugs, Bumpers, Grommets, Clips 	<ul style="list-style-type: none"> Automotive - Seals and Gaskets Consumer - Electronics Consumer - Floor Care General Purpose 	<ul style="list-style-type: none"> Home & Garden Industrial - Seals and Gaskets Printers
Uses	<ul style="list-style-type: none"> Automotive Applications Cell Phones Consumer Applications 	<ul style="list-style-type: none"> Gaskets Industrial Applications Printer Parts 	<ul style="list-style-type: none"> Seals
Agency Ratings	<ul style="list-style-type: none"> EU 2003/11/EC 	<ul style="list-style-type: none"> UL QMFZ2 	<ul style="list-style-type: none"> UL QMFZ8
RoHS Compliance	<ul style="list-style-type: none"> RoHS Compliant 		
Automotive Specifications	<ul style="list-style-type: none"> CHRYSLER MS-AR100 BMN DELCO ELEC M0010700018 	<ul style="list-style-type: none"> FORD WSD-M2D378-A4 GM GMPE/P.137 	<ul style="list-style-type: none"> VALEO VMS-8694
Color	<ul style="list-style-type: none"> Black 		
Form(s)	<ul style="list-style-type: none"> Pellets 		
Processing Method	<ul style="list-style-type: none"> Injection Molding 	<ul style="list-style-type: none"> Multi Injection Molding 	
Revision Date	<ul style="list-style-type: none"> 03/22/2006 		

Physical	Typical Value (English)	Typical Value (SI)	Test Based On
Specific Gravity	0.960	0.960	ASTM D792
Density	0.960 g/cm ³	0.960 g/cm ³	ISO 1183

Hardness	Typical Value (English)	Typical Value (SI)	Test Based On
Shore Hardness			ISO 868
Shore A, 15 sec, 73°F (23°C), 0.0787 in (2.00 mm)	49	49	

Elastomers	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Stress at 100% - Across Flow (73°F (23°C))	203 psi	1.40 MPa	ASTM D412
Tensile Stress at 100% - Across Flow (73°F (23°C))	203 psi	1.40 MPa	ISO 37
Tensile Strength at Break - Across Flow (73°F (23°C))	508 psi	3.50 MPa	ASTM D412

Typical properties: these are not to be construed as specifications.

© 2010 ExxonMobil. To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. You may not copy this document to a Web site. ExxonMobil does not guarantee the typical (or other) values. Analysis may be performed on representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no endorsement of any product or process, and we expressly disclaim any contrary implication. The terms, "we", "our", "ExxonMobil Chemical", or "ExxonMobil" are used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliates they directly or indirectly steward. ExxonMobil, the ExxonMobil Logo, the Interlocking "X" Device, and all other product names used herein are trademarks of ExxonMobil unless indicated otherwise.

**ExxonMobil Chemical Santoprene™ 111-45
Thermoplastic Vulcanizate**

Elastomers	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Stress at Break - Across Flow (73°F (23°C))	508 psi	3.50 MPa	ISO 37
Elongation at Break - Across Flow (73°F (23°C))	340 %	340 %	ASTM D412
Tensile Strain at Break - Across Flow (73°F (23°C))	340 %	340 %	ISO 37
Tear Strength - Across Flow (73°F (23°C), Die C)	62.8 lbf/in	11.0 kN/m	ASTM D624
Tear Strength - Across Flow 73°F (23°C), Method Bb, Angle (Nicked)	63 lbf/in	11 kN/m	ISO 34-1
Compression Set 73°F (23°C), 22.0 hr, Type 1	11 %	11 %	ASTM D395B
257°F (125°C), 70.0 hr, Type 1	35 %	35 %	
Compression Set 73°F (23°C), 22.0 hr, Type A	11 %	11 %	ISO 815
257°F (125°C), 70.0 hr, Type A	35 %	35 %	
Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Brittleness Temperature	-80 °F	-62 °C	ASTM D746
Brittleness Temperature	-80 °F	-62 °C	ISO 812
Electrical	Typical Value (English)	Typical Value (SI)	Test Based On
Dielectric Strength (0.0800 in (2.03 mm))	750 V/mil	30 kV/mm	ASTM D149
Dielectric Constant 73°F (23°C), 0.0780 in (1.98 mm)	2.40	2.40	ASTM D150
Dielectric Constant 73°F (23°C), 0.0780 in (1.98 mm)	2.40	2.40	IEC 60250
Injection	Typical Value (English)	Typical Value (SI)	
Drying Temperature	180 °F	82.2 °C	
Drying Time	3.0 hr	3.0 hr	
Suggested Max Moisture	0.080 %	0.080 %	
Suggested Max Regrind	20 %	20 %	
Rear Temperature	350 to 380 °F	177 to 193 °C	
Middle Temperature	355 to 390 °F	179 to 199 °C	
Front Temperature	355 to 400 °F	179 to 204 °C	
Nozzle Temperature	375 to 445 °F	191 to 229 °C	
Processing (Melt) Temp	380 to 465 °F	193 to 241 °C	
Mold Temperature	50.0 to 125 °F	10.0 to 51.7 °C	
Injection Rate	Fast	Fast	
Back Pressure	50.0 to 100 psi	0.345 to 0.689 MPa	
Screw Speed	100 to 200 rpm	100 to 200 rpm	
Clamp Tonnage	3.0 to 5.0 tons/in ²	41 to 69 MPa	
Cushion	0.125 to 0.250 in	3.18 to 6.35 mm	
Screw L/D Ratio	16.0:1.0 to 20.0:1.0	16.0:1.0 to 20.0:1.0	
Screw Compression Ratio	2.0:1.0 to 2.5:1.0	2.0:1.0 to 2.5:1.0	
Vent Depth	0.0010 in	0.025 mm	

Typical properties: these are not to be construed as specifications.

© 2010 ExxonMobil. To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. You may not copy this document to a Web site. ExxonMobil does not guarantee the typical (or other) values. Analysis may be performed on representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no endorsement of any product or process, and we expressly disclaim any contrary implication. The terms, "we", "our", "ExxonMobil Chemical", or "ExxonMobil" are used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliates they directly or indirectly steward. ExxonMobil, the ExxonMobil Logo, the Interlocking "X" Device, and all other product names used herein are trademarks of ExxonMobil unless indicated otherwise.

ExxonMobil Chemical Santoprene™ 111-45 Thermoplastic Vulcanizate

Injection Notes

Santoprene TPV is incompatible with acetal and PVC. An SPI/SPE #3 finish is recommended (do not polish). For more information regarding processing and mold design, please consult our Injection Molding Guide.

Aging	Typical Value (English)	Typical Value (SI)	Test Based On
Change in Tensile Strength in Air 302°F (150°C), 168 hr	-23 %	-23 %	ASTM D573
Change in Tensile Strength in Air 302°F (150°C), 168 hr	-23 %	-23 %	ISO 188
Change in Ultimate Elongation in Air 302°F (150°C), 168 hr	26 %	26 %	ASTM D573
Change in Tensile Strain at Break in Air 302°F (150°C), 168 hr	26 %	26 %	ISO 188
Change in Durometer Hardness in Air Shore A, 302°F (150°C), 168 hr	1.0	1.0	ASTM D573
Change in Shore Hardness in Air Shore A, 302°F (150°C), 168 hr	1.0	1.0	ISO 188

Additional Information

Values are for injection molded plaques, fan-gated, 102.0 mm x 152.0 mm x 2.0 mm (4.000" x 6.000" x 0.080").
Tensile strength, elongation and tensile stress are measured across the flow direction - ISO type 1, ASTM die C.
Compression set at 25% deflection.

Legal Statement

For detailed Product Stewardship information, please contact Customer Service.

This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use.

Processing Statement

Desiccant drying for 3 hours at 80°C (180°F) is recommended. Santoprene TPV has a wide temperature processing window from 175 to 230°C (350 to 450°F) and is incompatible with acetal and PVC. For more information, please consult our Material Safety Data Sheet and Injection Molding Guide.

Notes

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

For additional technical, sales and order assistance:

Worldwide and the Americas ExxonMobil Chemical Company 13501 Katy Freeway Houston, TX 77079-1398 USA 1-281-870-6050	Asia Pacific ExxonMobil Chemical Singapore Pte. Ltd. 1 HarbourFront Place #06-00 HarbourFront Tower One Singapore 098633 66-2163-8444	Europe, Middle East and Africa ExxonMobil Chemical Europe Hermeslaan 2 1831 Machelen, Belgium 420-239-016-274
--	--	---

Typical properties: these are not to be construed as specifications.

© 2010 ExxonMobil. To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. You may not copy this document to a Web site. ExxonMobil does not guarantee the typical (or other) values. Analysis may be performed on representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no endorsement of any product or process, and we expressly disclaim any contrary implication. The terms, "we", "our", "ExxonMobil Chemical", or "ExxonMobil" are used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliates they directly or indirectly steward. ExxonMobil, the ExxonMobil Logo, the Interlocking "X" Device, and all other product names used herein are trademarks of ExxonMobil unless indicated otherwise.